



Technical Data Sheet

Effective: 02/03/2020 Supersedes: 10/08/2018

Automotive Aftermarket Division

3M™ 37455 FC Epoxy Metal Filler

1) Part Numbers

3M™ 37455 FC Epoxy Metal Filler

2) Description and end uses

FC Epoxy Metal Filler 37455: 180 ml two-component u-TAH® Universal Cartridge uses a 2:1 mixing ratio (base to hardener).

3M™ 37455 is intended to be used as an automotive body repair material. This fast curing epoxy filler is capable of repairing imperfections such as dents in steel, galvanized steel and aluminum, for the final shaping on difficult-to-reach/rebuild areas or welded joints. It is designed to substitute traditional tin soldering and it is free of isocyanate, silicones and lead.

FC Epoxy Metal Filler is designed to be used with commercially available cartridge applicators that are equipped with a piston rod (manual, pneumatic with inlet pressure 5 – 5.5 bar, battery) and the 3M™ Static Mixing Nozzle (PN 51875).

3) Physical Properties

| Container | Two-component u-TAH® Universal Cartridge | |
|-------------|--|--------------------------------------|
| | Part A (Hardener) | Part B (Base) |
| Base | Fatty acid unsaturated, Dimere, Polymer | Bisphenol A/ Diglycidylether-Polymer |
| Consistency | Viscous paste | Viscous paste |
| Density | 1,02 g/cm ³ | 1,01 g/cm ³ |
| Colour | black | cream-white |



Technical Data Sheet

Effective: 02/03/2020 Supersedes: 10/08/2018

The following times have been determined with ambient air temperature and a substrate temperature at 20 – 25°C and are considered typical values.

Work Time: ~ 15- 20 min. @ 22 °C
Mix Nozzle dwell time: ~ 15- 20 min. @ 22 °C
Sand time: ~ 4 h @ 22 °C or
~ 10 - 20min. @ 70 °C Object temperature (IR Curing)

Usage temperature: 10 – 40 °C
Optimum temperature: 15 – 35 °C

Tipp for use: warming up the surface to ~30°C before material application will help to accelerate curing, particularly at cold ambient temperatures

4) Directions for Use

Preparation

Surfaces should be thoroughly de-greased and free from dirt and dust. Sand the damaged area with a P80-P120 abrasive disc. To remove any corrosion or broken paint, a suitable Fibre Disc or 3M™ Bristle Disc should be used. Wipe dust away and clean the surface with 3M™ 08984 General Purpose Adhesive Cleaner.

Wear appropriate personal protective equipment when working with FC Epoxy Metal Filler. Refer to the relevant MSDS and applicator user manual.

Application method

Installing the cartridge:

- Screw off coupling ring and remove cap
- Insert the cartridge into a suitable application gun
- Before attaching the mixer to the cartridge, squeeze out a small amount of material until both components run equally
- Attach static mixer
- Do not use the first 2-4 cm of extruded material, this might not be perfectly mixed. This instruction is directed to a new cartridge to allow initial equalisation, any further material is good to use.



Dispensing techniques:

- Material may be dispensed directly onto the damaged area, or a spreader or a mixing board.
- Proceed with application method (e.g. spreading) as desired.
- You may continue to dispense material until the normal material curing process clogs the mixing nozzle – typically after approximately 15 to 20 minutes. If more repair material is desired after curing has occurred, remove and install a new nozzle.
- Maximum finished thickness should not exceed 4-6 mm, maximum layer thickness should not exceed 2-3 mm.

Best practice application techniques to ensure minimal risk of pinholes:

Keep nozzle tip always in the material, place beads directly next to each other



A small amount of equalisation waste with a new nozzle is possible if previous material was expressed with high pressure or if a large amount was expressed before.

Always check that the colour of the material coming out is a shade of grey, if in doubt, discard the first couple of cm.

CAUTION: Be sure to replace nozzles containing fully or semi cured material to prevent damage to cartridge or nozzle or personal injury. If material is dispensed through nozzle containing cured material, re-equalisation of material might be needed. Dispose of uncured material in an approved waste stream.

Infra Red Curing



Technical Data Sheet

Effective: 02/03/2020 Supersedes: 10/08/2018

- Start the accelerate drying after gelling of 3M™ 37455 / ~ 15min after application
- The exothermic reaction of the fresh material could otherwise be triggered too quickly, which could generate blistering.
- Refer to and follow the manufacturer's instructions when using IR equipment for the accelerate curing of 3M™ FC Epoxy Metal Filler
- The following are typical figures provided for guidance
 - Short wave - 4 min at full power
 - 4:20:70 - 4 minutes total time - Temperature increase 20°C per minute
Maximum Object Temperature is 70°C
 - Medium wave - 5-10 min at full power

Distance from panel : Consult IR equipment manufacturers instructions

Next steps – following layers

If there is a need for an additional application / layer of 3M™ 37455, please repeat the following process steps:

- Application of 3M™ FC Epoxy Metal Filler
 - Material can be applied over itself without any difficulty
- Drying
- Surface grinding
 - Also workable with a body file

Next steps:

- Application of 2K Polyester Filler or Glaze
- Further processing at the repaired area can be overpainted according to the paint manufacturers guidelines.

5) Storage

18 months from original date of manufacture in the original sealed packaging between 10 °C – 25 °C. Refer to label for expiry date. Any opened cartridge can be stored with the used nozzle on for a few days; be sure to put a fresh nozzle on before using the cartridge again.

6) Safety

Read full instructions and material safety data sheet before use.

IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are



Technical Data Sheet

Effective: 02/03/2020 Supersedes: 10/08/2018

available via your stockiest. The supplier disclaims any liability where the user does not wear recommended personal protective equipment.

3M™ 37455 FC Epoxy Metal Filler is designed FOR PROFESSIONAL INDUSTRIAL USE ONLY.

7) Disclaimer

All statements, technical information and recommendations are based on tests we believe to be reliable as at the date of hereof, but the accuracy or completeness thereof is not guaranteed. Please ensure before using the product that it is suitable for your intended use. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, other than for fraudulent misrepresentation, 3M expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.

For Additional Health and Safety Information

| |
|---|
| 3M South Africa & Sub-Saharan Africa, 146A Kelvin Drive, Woodmead, Sandton, South Africa, Tel: (0861) 225536 |
| 3M (East) AG Representation Office Tirane, Rruga Sami Frasheri, Pallati i Ri Perxhola Kati 2 Ap2, 1000 Albania |
| 3M Arabia, LLC, Building 24-25 3M Saudi Arabia Zone C, Business Gate, Airport Road, Riyadh, Saudi Arabia |
| 3M Bulgaria, Mladost 4, Business Park, bl.4, 2nd floor, Sofia 1766, Bulgaria |
| 3M Česko, spol. s r.o., V Parku 2343/24, 148 00 - Praha 4, Czech Republic |
| 3M (East) AG, Branch office Croatia, Avenija Većeslava Holjevca 40, 10 000 Zagreb, Croatia, Tel: +385 1 2499750, www.3m.com.hr |
| 3M Egypt, Finance Center , New Cairo , Plot 140 , Banking Sector , 5th settlement , Cairo , Egypt |
| 3M Hellas MEPE, Automotive Aftermarket Division, 20 Kifisias Avenue, 151 25 Marousi, Greece, Phone: +30 210 68 85 300, innovation.gr@mmm.com, www.3M.gr |
| 3M Hungária Kft, Neumann János u. 1/E, 1117 Budapest, Hungary |
| 3M Israel, 91 Medinat Hayehudim St., Herzliya, Israel |
| 3M Kenya Ltd, Victoria Towers, 3rd Floor, Kilimanjaro Av, Upperhill, Kenya |
| 3M Gulf Limited, Ein El Mreisseh, Saint Charles City Center, 4th. Floor, P.O.Box: 11-5025, Riad el Solh, Beirut 1107 2180 Lebanon |
| 3M Minnesota Mining & Manufacturing Nigeria Limited, No 2 Sheraton Opebi Link Road, Ikeja, Lagos Nigeria |
| 3M Pakistan, Islamic Chamber of Commerce Building, ST-2/A, Block 9, KDA Scheme 5, Clifton, Karachi, Pakistan |
| 3M Poland, Al. Katowicka 117, Kajetany, 05-830 Nadarzyn, Poland, Telefon: +48 22 739 60 00, www.3m.pl/kontakt |
| 3M Gulf (Representation Office), Suhaim Bin Hamad St., Al Mana Towers Tower B, 2nd Floor, Office No.4, Doha Qatar, P.O.Box 14685 |



Technical Data Sheet

Effective: 02/03/2020 Supersedes: 10/08/2018

| |
|--|
| 3M Romania,12 Meneutului St., Bucharest Business Park, Building D, District 1 013713 Bucharest, Romania |
| 3M (East) AG, Representation Office Serbia, Airport City, Omladinskih brigada 90B, 11070 Belgrade, Serbia, Tel: +381 11 2209 400, www.3m.co.rs/3M/sr_RS/3m-south-east-europe/ |
| 3M Slovensko s.r.o., Polus Tower 2, Vajnorská 100/B, 83104 Bratislava |
| 3M (East) AG, Branch office Slovenia, Cesta v Gorice 8, 1000, Ljubljana, Slovenia, Tel: +386 1 2003 630, www.3m.com/3M/sl_SI/3m-south-east-europe/ |
| 3M Sanayi ve Ticaret As, Barbaros Mah., Mor Sümbül Sok., No:7/3F, 27-51, Nidakule Ataşehir Güney, 34746 Ataşehir, İstanbul, Turkey |
| 3M Gulf Limited, Dubai Internet City, Building No. 11, 3rd Floor, U.A.E |